



# Sanabel Alataa

For Paper and Cardboard Industries L.L.C

## TYPICAL CHARACTERISTICS

## QUALITY SPECIFICATIONS HIGH PERFORMANCE FLUTING

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE						
Basis Weight	g/m <sup>2</sup>	ISO 186	100	110	120	125	150	175	200
Moisture	%	ON-LINE	7.5						
CMT <sub>30</sub>	N	ISO 7263	190	200	220	230	270	-	-
SCT <sub>CD</sub>	kN/m	ISO9895	2.0	2.05	2.3	2.4	2.8	3.3	3.5

## TOLERANCE

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE						
Basis Weight	g/m <sup>2</sup>	ISO 186	100	110	120	125	150	175	200
Mean Basis Weight	%		± 3%						
Moisture	%	ON-LINE	7.5						
Mean Moisture	%		± 1						
CMT <sub>30</sub>	N	ISO 7263	± 10%						
SCT <sub>CD</sub>	kN/m	ISO9895	± 10%						

## PRODUCT TECH. DATA

Reel Width, Preferably Trimmings ..... As specified  
 Reel Diameters ..... As specified  
 Core Inside Diameter ..... 100 – 100.2 mm  
 Quantity Tolerance ..... As specified



9001:2015



45001:2018



14001:2015



19465:2015

## STORAGE

It is advisable to store paper in a well-ventilated area that is cool and dry, with adequate covering. Paper should be kept away from any materials that are flammable.  
 Testing conditions for paper should be maintained at a temperature of 23 °C and a relative humidity of 50%.



IGBCGRS240201

