



Sanabel Alataa

For Paper and Cardboard Industries L.L.C

TYPICAL CHARACTERISTICS

QUALITY SPECIFICATIONS

TESTLINER

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE						
Basis Weight	g/m ²	ISO 186	110	120	125	150	175	200	
Moisture	%	ON-LINE	7.5						
Burst Strength	Kg/cm ²	ISO 2759	2.9	3.15	3.20	3.70	4.4	5.0	
SCT _{CD}	kN/m	ISO9895	2.0	2.05	2.2	2.4	2.8	3.2	
COBB	g/m ²	ISO 535	50						

TOLERANCE

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE						
Basis Weight	g/m ²	ISO 186	110	120	125	150	175	200	
Mean Basis Weight	%		± 3%						
Moisture	%	ON-LINE	7.5						
Mean Moisture	%		± 1						
Burst Strength	Kg/cm ²	ISO 2759	± 10%						
SCT _{CD}	kN/m	ISO9895	± 10%						
COBB	g/m ²	ISO 535	± 10%						

PRODUCT TECH. DATA

Reel Width, Preferably Trimmings As specified
 Reel Diameters As specified
 Core Inside Diameter 100 – 100.2 mm
 Quantity Tolerance As specified



9001:2015



45001:2018



14001:2015



19465:2015

STORAGE

It is advisable to store paper in a well-ventilated area that is cool and dry, with adequate covering. Paper should be kept away from any materials that are flammable.
 Testing conditions for paper should be maintained at a temperature of 23 °C and a relative humidity of 50%.



IGBCGRS240201

