



Sanabel Alataa

For Paper and Cardboard Industries L.L.C

TYPICAL CHARACTERISTICS

QUALITY SPECIFICATIONS SEMI-CHEMICAL FLUTING

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE				
Basis Weight	g/m ²	ISO 186	110	125	140	150	160
Moisture	%	ON-LINE			7.5		
SCT _{CD}	kN/m	ISO 9895	2.15	2.42	2.73	2.82	3.15
CMT ₃₀	N	ISO 7263	235	270	300	331	355
CCT ₃₀	kN/m	ISO 16945	1.8	2.0	2.2	2.4	2.6
COBB	g/m ²	ISO 535			35		

TOLERANCE

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE				
Basis Weight	g/m ²	ISO 186	110	125	140	150	160
Mean Basis Weight	%				± 3%		
Moisture	%	ON-LINE			7.5		
Mean Moisture	%				± 1		
SCT _{CD}	kN/m	ISO 2759			± 10%		
CMT ₃₀	N	ISO 9895			± 10%		
CCT ₃₀	kN/m	ISO 16945			± 10%		
COBB	g/m ²	ISO 535			± 10%		

PRODUCT TECH. DATA

Reel Width, Preferably Trimmings As specified
 Reel Diameters As specified
 Core Inside Diameter 100 – 100.2 mm
 Quantity Tolerance As specified



9001:2015



45001:2018



14001:2015



19465:2015

STORAGE

It is advisable to store paper in a well-ventilated area that is cool and dry, with adequate covering. Paper should be kept away from any materials that are flammable.
 Testing conditions for paper should be maintained at a temperature of 23 °C and a relative humidity of 50%.



IGBCGRS240201



Jordan – AlQastal . Phone. +962792920888 . Fax. +962792920555
info@Khattab.group . www.Khattab.group . P.O Box 16197